

한국물리학회

회보

BULLETIN OF THE KOREAN PHYSICAL SOCIETY

제21권 제1호

제79회 정기총회 프로그램, 논문초록집

2003년 4월

사단
법인 한국물리학회

THE KOREAN PHYSICAL SOCIETY

$\text{Ti}_{0.995}^{57}\text{Fe}_{0.005}\text{O}_2$ 김철성, 이희민, 심인보, 김성백¹, 최용남¹, 이창희¹(국민대학교 물리학과. ¹한국원자력연구소.) We investigated magnetic behavior of TiO_2 with only a minute amount of Fe and separated contributions of the ferromagnetic and the paramagnetic phases to the magnetization. $\text{Ti}_{0.995}^{57}\text{Fe}_{0.005}\text{O}_2$ compounds were fabricated using the chemical solution method. The x-ray and neutron diffraction patterns for the sample showed a pure anatase single phase with a tetragonal structure, without any segregation of Fe into particulates within the instrumental resolution limit. Magnetic properties were characterized by the vibrating sample magnetometer (VSM) and Mössbauer spectroscopy with a $^{57}\text{Co}(\text{Rh})$ source. Room temperature magnetic hysteresis(M-H) curves showed an obvious ferromagnetic behavior and the magnetic moment per Fe atom under the applied field of 1 T was estimated to be about $0.067 \mu_B$, verified using Mössbauer measurement. Mössbauer spectra of $\text{Ti}_{0.995}^{57}\text{Fe}_{0.005}\text{O}_2$ were taken at various temperatures ranging from 14 to 295 K. Results showed that the ferromagnetic (sextet) and the paramagnetic phase (doublet) coexisted in all temperature ranges. The isomer shift values are attributed to the Fe^{3+} state of iron that was present in the sample. Separation of the ferromagnetic and the paramagnetic phase of the samples was characterized by Mössbauer technique. The occupied area ratio of the ferromagnetic phase was about 64 and 51 %, at 14 and 295 K, respectively. This result corresponded with M-H curves referred above. The observed small magnetic moment in

the M-H curves were fundamentally attributable to paramagnetic phase as well as ferromagnetic phase.