


AMC2008

Asian Magnetism Conference 2008

December 10-13, 2008, Paradise Hotel, Busan, Korea



Hosted by

The Korean Magnetism Society

Sponsored by

Korea Research Foundation

Korea Science and Engineering Foundation

Korean Federation of Science and Technology Societies

The Korean Magnetism Society

BS16

Stress Effects of CoCr_2O_4 Film on MgO and MgAl_2O_4 Grown by RF-Sputtering Process

Hoon Ko, Kang Ryong Choi, Seung-Iel Park, In Bo Shim, Sam Jin Kim, and Chul Sung Kim*

Department of Physics, Kookmin University, Seoul 136-702, Korea

*Corresponding author: Chul Sung Kim, e-mail: cskim@kookmin.ac.kr

In multiferroic thin films, ferromagnetic and ferroelectricity coexist[1,2]. CoCr_2O_4 film was deposited on MgO and MgAl_2O_4 substrates by rf-sputtering process. The films were prepared at rf-magnetron sputtering power of 50W and a pressure of 10 mtorr (20 sccm in Ar), substrate temperatures of 550°C. The crystal structure was determined to be spinel ($Fd3m$) structure by means of X-ray diffraction (XRD) with $\text{K}\alpha$ Cu radiation. The thickness and morphology of films were measured by scanning electron microscopy (SEM) and atomic force microscopy (AFM). The magnetic properties were measured using a Superconducting Quantum Interference Device (SQUID). The ferrimagnetic transitions were observed about 82 K, which was determined as Néel temperature, but magnetic behavior shows different. The results of each other magnetic property can be explained by stress effects between CoCr_2O_4 and substrates of MgO and MgAl_2O_4 .

REFERENCES

- [1] M. Gajek, et al. Nature Mater. 6, 296 (2007).
- [2] R. Ramesh, et al. Nature Mater. 6, 21 (2007).

BS17

Magnetic Refrigeration Properties of $\text{La}_{0.8}\text{Ca}_{0.2}\text{Mn}_{0.99}\text{Fe}_{0.01}\text{O}_3$

Sun Chun Hong¹, Sam Jin Kim¹, Eun Joo Hahn², Seung-Iel Park¹, and Chul Sung Kim^{1*}

¹Department of Physics, Kookmin University, Seoul 136-702, Korea

²Department of Physics, Suwon University, Hwaseong 445-743, Korea

*Corresponding author: Chul Sung Kim, e-mail: cskim@kookmin.ac.kr

The crystallographic and magnetic properties of $\text{La}_{0.8}\text{Ca}_{0.2}\text{Mn}_{0.99}\text{Fe}_{0.01}\text{O}_3$ have been studied using x-ray diffraction (XRD), vibrating sample magnetometer (VSM) and Mössbauer spectroscopy measurements. The $\text{La}_{0.8}\text{Ca}_{0.2}\text{Mn}_{0.99}\text{Fe}_{0.01}\text{O}_3$ sample was prepared by sol-gel method with starting materials La-nitrate, Ca-nitrate, Mn-acetate and ^{57}Fe -powder. The sample was annealed at 1000°C under O_2 atmosphere. Fig. 1 a) and b) show the x-ray refinement and temperature dependence of magnetization, respectively.




Fig. 1. a) Rietveld refinement of XRD pattern, b) temperature dependence of magnetization $M(T)$ measured at 5 kOe for $\text{La}_{0.8}\text{Ca}_{0.2}\text{Mn}_{0.99}\text{Fe}_{0.01}\text{O}_3$.

The crystal structure of $\text{La}_{0.8}\text{Ca}_{0.2}\text{Mn}_{0.99}\text{Fe}_{0.01}\text{O}_3$ was found to be orthorhombic ($Pnma$) structure with lattice constants $a_c = 5.486 \text{ \AA}$, $b_c = 7.761 \text{ \AA}$, and $c_c = 5.510 \text{ \AA}$ at room temperature. The Curie temperature (T_c) is determined to be 185 K by zero field cooled (ZFC) magnetization curve under 5 kOe applied field. Mössbauer spectrum at 4.2 K was fitted with two independent magnetic components of the magnetic hyperfine fields $H_{f1} = 526 \text{ kOe}$ and $H_{f2} = 501 \text{ kOe}$. Mössbauer spectra shows that the linebroadening and the ratio of the absorption areas is changed below T_c . The maximum value of magnetic entropy changes, $[\Delta S_{m,max}]$ is 0.54 J/kg·K at 155 K, under 5 kOe applied field [1]-[2].

REFERENCES

- [1] S. Stadler, M. Khan, J. Mitchell, N. Ali, I. Dubenko, A.Y. Takeuchi, and A.P. Guimarães, Appl. Phys. Lett. 88, 192511 (2006).
- [2] Z. B. Guo, Y. W. Du, J. S. Zhu, H. Huang, W. P. Ding, and D. Feng, Phys. Rev. Lett. 78, 1142 (1997).